

# PP

High Strength/high Heat Resistance

## ▶ HJ730

### ● Description

**HJ730** is a highly isotactic Homo PP(HIPP) with high crystal-line properties compared to normal Homo PP. The product's crystalline properties have enhanced its strength and heat resistance. HJ730 is highly useful for use in electrical/electronic appliances and high strength automobile parts which are exposed to lengthy periods of high temperatures.

### ● Characteristics

Unique balance of flowability and impact resistance: processing of large scale parts

- ▶ High strength → thin injection molded products may be formed
- ▶ Ultra-high heat resistance → high service temperature
- ▶ High crystallinity → suitable for high speed processing
- ▶ Good surface hardness → excellent scratch resistance
- ▶ Good pigment dispersion → allows for dry coloring

### ● Applications

- ▶ Home appliance such as coffee maker, kettle, etc

## ● **Physical Properties**

Typical Properties	Method (ASTM)	Unit	HJ730
Melt flow index	D1238	g/10min	20
Density	D1505	g/cm <sup>3</sup>	0.91
Tensile strength at yield	D638	kg/cm <sup>2</sup>	370
Elongation at break	D638	%	200
Flexural modulus	D790	kg/cm <sup>2</sup>	17,000
Izod impact strength 23 °C	D256	kgcm/cm	3
Rockwell hardness	D785	R-scale	105
Heat distortion temp.	D648	°C	120

\* Data shown above are representative values for reference purposes only, and not to be construed as specifications.

## ● **Food Contact Application**

- ▶ Hanwha Total HJ730 meets the FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for food contact.
- ▶ In case you might need additional technical or regulatory information, please contact Hanwha Total Polymer Technical Service Team.

## ● **Contacts**

### ▶ **Product Information & Technical Services**

103, Dokgot 2-ro, Daesan-eup, Seosan-si, Chungcheongnam-do,  
Korea, 31900

TEL : 82-41-660-6190      FAX : 82-41-660-6189

### Disclaimer

*This document is copyright of Hanwha Total petrochemicals Co., Ltd. Any and all information and the values in this document are typical properties for reference, not to be confused with, or regarded as specification. Customers are responsible for determining whether our products and information are suitable for their particular purpose and for ensuring that Customer's location and handling practices are in compliance with laws and regulations. HANWHA TOTAL assumes no obligation or liability for the information in this document. NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY HANWHA TOTAL. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. HANWHA TOTAL is entitled to alter, change or modify any of the content herein at any time without prior notice, but not under any duty to do so.*